

## WHITE PORTLAND-LIMESTONE CEMENT

BONDCRETE UNICORN Brand	
Type	CEM II 32.5R
Strength class	32.5R
Fe <sub>2</sub> O <sub>3</sub>	0.2%
SO <sub>3</sub>	2.3%
Chloride	0.01%
L.O.I	15%
Insoluble residue	0.2%
Equivalent alkalies (Na <sub>2</sub> O)	0.3%
Fineness (Blaine)	4500cm <sup>2</sup> /g
Le Chatelier expansion	2mm
2 day strength	20.0 MPa
28 day strength	40.0 MPa
Initial setting time (Vicat)	140min
Whiteness (Hunter)	93.0